



- **Weight per gallon:** 8.8-9.0 lb.
- **Pigment type:** Variable/Dependent upon Color
- **Flash Point:** 110°F
- **Volatile Organic Content (VOC):** 339 g./liter
- **Viscosity:** 280-350 cP
- **Theoretical coverage:** 350-450 sf/gal
- **Solids by volume:** 62.5%
- **Recommended dry film thickness:** 2-4 mils DFT (applied in 1-2 wet coats)
- **Temperature Resistance:** 314°F Continuous
- **Chemical Resistance:** Excellent
- **Recoatability:** With ColorShell or Clear Shot after 4-48 hours.
- **Color:** ANSI Compliant OSHA Safety Colors: Red, Orange, Yellow, Green, Blue, Purple
- **Finish:** Gloss
- **Cure Time:** Handle: 2-4 Hours; Touch: 2-4 Hours. Depending on ambient temperature and relative humidity. Recoat: 4-48 hours. Cure time varies with relative humidity, temperature and thickness of film (48-72 hours)
- **Shelf Life:** 2 years, after ship date, unopened, stored between 50°-100°F
- **Application Temperature:** 32°F-110°F (0°C-43°C)
- **Compatibility:** Compatible with all coatings that are compatible with MCUs (Moisture-cured Urethane); always refer to the coating manufacturer guidelines for application and compatibility.

Typical Uses

High performance protection for steel and iron applications, such as industrial, marine, farm, automotive, or any place where rust is a problem.

Product Description

Single component, aliphatic moisture cured urethane, gloss topcoat; ColorShells can be applied over painted or unpainted surfaces and can be used as a stand-alone protective coating that will protect your iron and steel. For the ultimate protection, apply ColorShell as a topcoat over our patented Rust Bullet Standard or Rust Bullet Automotive Formulas. ColorShells are UV Resistant, scratch and chip resistant. Rust Bullet ColorShells can be brushed, rolled or sprayed.

Advantages of ColorShell

- Easily applied and “forgiving” under less than desirable application conditions
- Can be applied on rusted or clean surfaces
- Single component
- Excellent resistance to weather and mechanical abuse
- Excellent chemical resistance
- Excellent abrasion resistance
- Excellent adhesion
- Excellent UV resistance
- Self Leveling
- Flexible

Safety Information

Avoid ingestion, contact with skin or eyes. The use of safety glasses and chemical gloves is recommended. When brushing or rolling or spraying, appropriate NIOSH approved respiratory protection is recommended. See [Safety Data Sheet](#) for complete safety data before use available at www.RustBullet.com. It is the applicator's responsibility to understand these safety precautions and the work environment, to protect themselves and/or others.

Surface Preparation

Surface must be free of contaminates, such as, loose rust, oil, grease, wax, moisture etc. This may be achieved by light scraping; a detergent or solvent wipe may be used if necessary. For more information:

RUST BULLET LLC ~ 300 Brinkby Avenue, Suite 200, Reno, NV 89509 USA (800) 245-1600, (775) 829-5606 www.rustbullet.com
Information contained herein is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of use are beyond our control, Rust Bullet, LLC (the Company), disclaims any liability incurred in connection with the use of our products and information contained herein. No person is authorized or empowered to make any statement or recommendation not contained herein, any such statement or recommendation so made shall not bind the Company. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use. The information is furnished upon the condition that the recipient shall make his own determination concerning suitability for his particular application.